



Suprasil® 310 – Premium Synthetic Quartz Glass Tubes for Deep UV Applications

Disinfection and cleaning with ultraviolet light is a cost-effective and environmentally friendly alternative to conventionally used chemical processes. Especially the deep UV radiation is becoming a more and more important tool in modern industrial applications. In LCD and semiconductor industries high energy 172 nm UV radiation is used for surface cleaning and processing of wafers and flat panel displays. Other application examples for 172 nm radiation are photochemical vapour deposition, surface activation and photochemistry. The materials specialist Heraeus provides premium synthetic quartz glass especially for deep UV applications.


Heraeus features:

- full synthetic quartz glass tubes for 172 nm applications (furnace cut, machine cut, fire polished, domed)
- highest transmission
- longest lifetime
- outstanding chemical purity
- technical product support
- flexible order quantities
- customized tube size: OD 3 – 350 mm diameter

Suprasil® 310


Typical transmission spectrum of Suprasil® 310

thickness: 2 mm



Heraeus provides premium quartz glass tubes for UV and deep UV applications with superior visual quality. These tubes have a superior transmission and a significantly improved lifetime compared to standard natural quartz glass tubes. Supporting highest UV output over a very long operation time Heraeus synthetic tubes provide highest reliability for your products and lower operational costs.

Transmission of different quartz glass types at 172 nm as a function of irradiation time



Typical impurity content in weight ppm (µg/g)

Li	Na	K	Mg	Ca	Fe
<0.01	<0.05	<0.01	<0.005	<0.05	<0.02
Cu	Cr	Mn	Al	Ti	
<0.01	<0.005	<0.005	<0.05	<0.05	

A. Schreiber, B. Kühn, E. Arnold, F.-J. Schilling, H.-D. Witzke, Radiation resistance of quartz glass for VUV discharge lamps, J. Phys. D: Appl. Phys. 38 (2005) 3242–3250

Suprasil® 310 features

Wavelength range	> 160 nm
Optical transmission	Outstanding transmission in the deep UV < 200 nm (80% @ 172 nm for 2 mm thickness)
Resistance to deep UV radiation	Withstands even aggressive 172 nm radiation
Application examples	Lamp envelopes and sleeves for: <ul style="list-style-type: none"> ■ Cleaning of surfaces, e.g. in processing of semiconductor wafers and flat panel displays ■ Photochemical vapour deposition ■ Activation of surfaces ■ Changes in structure and composition of surfaces ■ Photochemistry
Lamp types	■ 172 nm excimer lamps ■ deep UV lamps
Visual quality	Outstanding visual quality, almost free of any bubbles and inclusions
Availability/MOQ	10 kg

Europe
Heraeus Quarzglas GmbH & Co. KG
Heraeus Conamic
 Lamp Materials
 Reinhard-Heraeus-Ring 29,
 63801 Kleinostheim
 Phone +49 (6181) 35-62 34
 conamic.lampmaterials
 @heraeus.com

USA
Heraeus Quartz
North America LLC
Heraeus Conamic
 Sales Lamp Materials
 1520 Broadmoor Blvd., Ste. F
 Buford, GA 30518
 Phone +1 (678) 714-4350
 conamic.lampmaterials
 @heraeus.com

China
Heraeus ShinEtsu
Quartz (China) Inc.
 905, Zendai Cube Edifice,
 No.58 Changliu Road, Pudong
 Shanghai, 200122 China
 Phone +86 (21) 68672266-809
 conamic.lampmaterials
 @heraeus.com

Japan
Shin-Etsu
Quartz Prod. Co., Ltd.
 Shinjuku San-Ei Bldg.,
 12th Floor Shinjuku-Ku
 Tokyo 160
 Phone +81 (0) 333-48-1913
 d3sales@sqp.co.jp