
Heraeus



Foldable | Conductive | Durable

Clevios™ HY E — The Next-Generation Material for Foldable Touch Displays

Clevios™ HY E is a unique hybrid material made from conductive polymers (PEDOT) and silver nanowires (AgNW). It combines the strengths of both technologies: PEDOT provides improved flexible properties, invisible patterning, intrinsic ESD protection, and improved sheet resistance isotropy, while silver nanowires realize low sheet resistances and high transmissions of the coated transparent electrode layers.

- Over 300,000 times stable bending at 1 mm radius for reliable foldable touch displays
- Invisible wet-patterning technology for superior optical properties of touch sensors
- 30-150 Ohm/sq with excellent SR isotropy
- Wet-coating or printing on plastics, e.g. PET, CPI, PC


CLEVIOSTM HY E -

The Next-Generation Material for Foldable Touch Displays

Foldable - Conductive - Durable - Solution Processible **Properties** Sample 100 Aqueous dispersion, ready to use ■ CleviosTM OC 1 (\approx 0,7 µm) 90 ■ Clevios[™] HY E (≈ 0,15 μm) Cost effective wet-coating, e.g. by slot-die coating 80 Good adhesion to PET, CPI, PC □ PET Substrate (25 µm) 60 SR [Ω/□] ■ Protective overcoat CleviosTM OC 1 50 ■ Low sheet resistance, adjustable from $15-150 \Omega/\Box$ 40 30 Excellent SR isotropy and built-in ESD protection **Bending test** > 300,000x20 Bending radius: 1 mm High transmission > 95 % 10 • Stable SR after > 300 k bendings at R = 1 mm radius 100.000 200.000 300.000

Patterning of Clevios™ HY E

- Laser and wet patternable



Applications for Clevios[™] HY E include foldable touch displays, OLED and OPV.

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis at least must include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Heraeus. All information is given without warranty or guarantee. It is expressly understood and agreed that the customer assumes and hereby expressly releases

Heraeus from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance and information. Any statement or recommendation not contained herein is unauthorized and shall not bind Heraeus. Nothing herein shall be construed as a recommendation to use any product in conflict with pathets covering any material or its use. No license is implied or in fact granted under the claims of any patent. Properties of the products referred to herein shall as general rule not be classed as information on the properties of the item for sale. In case of order please refer to issue number of the respective product data sheet. All deliveries are based on the latest issue of the product data sheet and the latest version of our General Conditions of Sale and Delivery.

bending cycles (R=1mm, outward)

Heraeus Deutschland GmbH & Co. KG

Heraeus Epurio
Building B202, Chempark
51368 Leverkusen, Germany
clevios@heraeus.com
www.clevios.com I www.heraeus.com

