

## Technical Data Sheet



**Product Type:** No Clean Solder Paste  
**Product Name:** Microbond® SMT701  
**Product ID:** FC701 SAC305-88P4

### Description

FC701 SAC305-88P4 solder paste is a state-of-the-art lead free no clean solder paste that promotes outstanding wetting and minimizes soldering defects. The FC701 flux system is specifically optimized for lead free alloys, e.g. Sn/Ag/Cu. This formula provides superior performance on a variety of surfaces finishes and leaves behind a clear residue.

### Key Benefits

- Good wetting on OSP, HASL surface and Al board
- Good void performance
- Transparent residue

### Applications

- Printing

### Product Code and Alloy

Product Code					Powder Properties		
Paste	Alloy	Metal Content	*Viscosity	Powder Type	Particle Size	Alloy	Melting Point
FC701	SAC305	88%	P	4	20 – 38 µm	Sn96.5/Ag3/Cu0.5	217 °C

\*D = Dispense grade P = Print grade L = Dipping/Jetting grade, Low


### Flux Activity

Activity Level (J-STD 004)	Classification
ROLO	No Clean/ Solvent Clean

### Halogen Content

Halogen-Zero (No halogen added in the flux)
Tolerances: Halogen < 50 ppm; measured according to BS EN 14582

### Recommended Reflow Profile



\* Graph not drawn to scale

Recommended Profile	
Average Ramp Rate	1 – 3 °C/s
Peak Temperature	15 °C (min) – 40 °C (max) above Melting Temperature
Time above liquidus	45 – 90 s
Reflow Atmosphere	Reflow in Air or in N <sub>2</sub> with < 2000 ppm O <sub>2</sub>
Type 3 – 5	

The descriptions and engineering data shown here have been compiled by Heraeus using commonly-accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for a particular application)

## Technical Data Sheet

### Cleaning Instructions

After reflow flux residues may remain on the circuit and do not need to be washed. For cleaning of wet paste or if desired for cleaning of flux residues Zestron and Vigon cleaners can be used – see separate cleaning recommendations.

### Storage

- Store the solder paste in tightly-sealed containers and avoid exposure to sunlight and high humidity
- Max expiration date: please refer to the expiry date on the label of the packaged product
- Storage condition in the refrigerator at 2 - 10 °C

### Paste Preparation

- Remove paste from fridge: Before opening the package, leave paste for at least 4 hours (depending on jar/ cartridge size) at room temperature, so that paste warms up
- Do not open jar/cartridge while paste is cold to prevent condensation
- Do not heat the paste beyond room temperature

**Heraeus Electronics**  
Heraeus Deutschland GmbH & Co. KG  
Heraeusstraße 12 – 14  
63450 Hanau, Germany  
[www.heraeus-electronics.com](http://www.heraeus-electronics.com)

**Americas**  
Phone +1 610 825 6050  
[electronics.americas@heraeus.com](mailto:electronics.americas@heraeus.com)

**Asia Pacific**  
Phone +65 6571 7677  
[electronics.apac@heraeus.com](mailto:electronics.apac@heraeus.com)

**China**  
Phone +86 21 3357 5457  
[electronics.china@heraeus.com](mailto:electronics.china@heraeus.com)

**Europe, Middle East and Africa**  
Phone +49 6181 35 3069, +49 6181 35 3627  
[electronics.emea@heraeus.com](mailto:electronics.emea@heraeus.com)