

## Technical Data Sheet

### THICK FILM MATERIALS

Product Type: Conductors

Product Name: C6012



#### Solderable AuPdPt Conductor Paste for Fuel Sensors

##### Description

C6012 is a screen printable, solderable Gold / Palladium / Platinum conductor paste for fuel sensor applications.

C6012 is optimized in hardness and surface density. It shows excellent printability resulting in high line definition and smooth surface under various drying conditions.

##### Key Benefits

- Most suitable material for low sulphur fuel application because of absence of silver
- Very smooth fired surface which exhibits very durable mechanical resistance and chemically extremely resistant
- Solderable with customary solder alloys
- Free of cadmium and nickel
- REACH<sup>3</sup> and ROHS<sup>4</sup> compliant

##### Processing

- 1) Spatulate well prior to processing.

When stored in a refrigerator, allow paste to come to room temperature prior to opening, to avoid condensation.

- 2) Print through a 200 – 325 mesh stainless steel screen. 0.03 – 0.04 mm Ø wire and 20 – 30 µm emulsion.
- 3) Level at room temperature for 10 minutes.
- 4) Dry at max. 150 °C for 8 – 10 minutes.
- 5) Fire at 850 °C (peak) for 10 minutes, and with a total firing cycle time of c. 30 – 60 minutes.

##### Thinner

HVS 100

##### Typical Properties (Paste)

Form	Pseudoplastic paste
Viscosity	70 – 90 Pas (25 °C, D = 50/s)
Solids	85.0 % ± 1.0 %
Coverage	c. 65 cm <sup>2</sup> /g (at FFT 10 µm)
Shelf Life	6 months from date of shipment with correct storage (in a dry, cool (5 – 25 °C) and dark place with container tightly shut).

##### Typical Properties (Fired)<sup>1</sup>

Fired Film Thickness <sup>2</sup> (FFT)	7.5 – 11.5 µm
Line Definition <sup>2</sup>	≥ 125 µm
Resistivity <sup>2</sup>	≤ 85 mΩ/□ (FFT: 10 µm)
Adhesion <sup>2</sup> (Sn62/Pb36/Ag2)	≥ 20 N (16h at RT)
Solderable with	Sn62/Pb36/Ag 2 Sn96.5/Ag3.5 Sn63/Pb37

##### Typical adhesion data

Storage	Solder Alloy		
	Ag2	Ag3.5	Pb37
Initial	≥ 20 N	≥ 20 N	≥ 20 N
48 h / 100 °C	≥ 20 N	≥ 20 N	≥ 20 N
500 h / 100 °C	≥ 20 N	≥ 18 N	≥ 20 N
1000 h / 100 °C	≥ 18 N	≥ 15 N	≥ 18 N

## Technical Data Sheet



### Solderable AuPdPt Conductor Paste for Fuel Sensors

#### Legend:

- 1) Typical properties based on laboratory test methods. For optimum results all materials should be fired in a profiled furnace supplied with dried, hydrocarbon and other contaminant free air (PP-1).
- 2) Measured after printing with a 325 mesh steel screen; screen thickness and emulsion thickness combined was c. 75 µm, and the resultant printed track was 500 µm wide.
- 3) REACH compliant according to the latest \*\* Annex XIV to Regulation (EC) of the European Parliament and of the council on the Registration, Evaluation, Authorisation and Restriction of Chemicals ("REACH") by European Chemicals Agency and its subsequent amendments; the material does not contain any substance listed in Annex XIV.
- 4) RoHS compliant according to the latest \*\* Directives (European Union) of Restriction of Hazardous Substances ("RoHS") and its subsequent amendments (including the exceptions related to Pb)

\* See the data sheet issue date (DD/MM/YY) as reference of validity of latest edition which is available on request

**Heraeus Electronics**  
Heraeus Deutschland GmbH & Co. KG  
Heraeusstraße 12 – 14  
63450 Hanau, Germany  
www.heraeus-electronics.com

**Americas**  
Phone +1 610 825 6050  
electronics.americas@heraeus.com

**China**  
Phone +86 21 3357 5457  
electronics.china@heraeus.com

**Asia Pacific**  
Phone +65 6571 7677  
electronics.apac@heraeus.com

**Europe, Middle East and Africa**  
Phone +49 6181 35 3069, +49 6181 35 3627  
electronics.emea@heraeus.com