

Technical Data Sheet

THICK FILM MATERIALS

Product Type: Dielectrics

Product Name: IP6080A

CELCION

Dielectrics for Aluminum Substrates



Description

IP6080A, part of the Celcion material system, is a cadmium free single part dielectric paste which produces a dense, grey, hermetic fired film. IP6080A is compatible with 3000 and 6000 grade aluminum substrates. Its unique glass system dramatically reduces bowing on aluminum while providing high breakdown strength up to 75 μm of dielectric. It is compatible with C8829A and C8829D Ag conductors.

Key Benefits

- REACH¹ and ROHS² compliant
- Excellent electrical properties
- High breakdown voltage
- Compatible with Aluminum substrates

Typical Properties

Dielectric Constant

< 20 at 1 KHz

Dissipation Factor

< 0.5 % at 1 KHz

Insulation Resistance

> 10⁹ Ω at 100 DC

Breakdown Voltage

> 1000 V DC per mil
(2 individually fired layers)

Bowing Deflection

2 PDF layers – 2" x 2" Al substrate (full coverage print)
< 0.0180 inch on 2mm 3003 – H14 aluminum alloy
< 0.0042 inch on 2mm 6061 – T6 aluminum alloy

Viscosity

40 – 80 Kcps, Brookfield RVT,
SC4-14 spindle with 6R utility cup at 10 rpm, 25 °C

Solids

72.0 \pm 2.0 %

Recommended Processing Guidelines

Printing

165 mesh stainless steel screen
0.5 mil emulsion thickness
Allow wet prints to level at room temperature for 10 minutes before drying
Three individually fired layers with a total thickness of at least 50 μm will be necessary to achieve the optimum performance level

Coverage

155 cm²/g at 40 μm wet film thickness

Drying

150 °C for 15 minutes

Firing

570 °C as measured on substrate
Dwell time of 2 – 20 minutes,
dependent on application/substrate mass

Thickness

Dried:	35 – 40 μm (1 layer)
Fired:	25 – 30 μm (1 layer)
	50 – 60 μm (2 layers)

Thinner

RV-507

Warranty

Material guaranteed to meet specifications for 6 months from date of shipment.

Storage

Store in a dry location at 5 – 10 °C to ensure proper performance of shelf life.

Allow paste to come to room temperature prior to opening. Spatulate well before using.

Technical Data Sheet

CELCION

Dielectrics for Aluminum Substrates



Legend:

1) REACH compliant according to the latest ** Annex XIV to Regulation (EC) of the European Parliament and of the council on the Registration, Evaluation, Authorisation and Restriction of Chemicals ("REACH") by European Chemicals Agency and its subsequent amendments; the material does not contain any substance listed in Annex XIV.

2) RoHS compliant according to the latest ** Directives (European Union) of Restriction of Hazardous Substances ("RoHS") and its subsequent amendments (including the exceptions related to Pb)

** See the data sheet issue date (DD/MM/YY) as reference of validity of latest edition which is available on request

Heraeus Electronics
Heraeus Deutschland GmbH & Co. KG
Heraeusstraße 12 – 14
63450 Hanau, Germany
www.heraeus-electronics.com

Americas
Phone +1 610 825 6050
electronics.americas@heraeus.com

China
Phone +86 21 3357 5457
electronics.china@heraeus.com

Asia Pacific
Phone +65 6571 7677
electronics.apac@heraeus.com

Europe, Middle East and Africa
Phone +49 6181 35 3069, +49 6181 35 3627
electronics.emea@heraeus.com