# Heraeus

## **Technical Data Sheet**



# THICK FILM MATERIALS

**Product Type:** Conductors

**Product Name: C2240** 







Silver / Palladium Conductor Paste

#### Description

C2240 is a lead free 4 : 1 Ag / Pd conductor paste which exhibits a high density, high reliability and good fine line resolution. It fires to a smooth surface and is mechanically durable and chemically resistant.

Due to these characteristic C2240 is a recommended material for application such as fuel sensors.

#### **Key Benefits**

- Excellent conductivity, leach resistance and resistance to silver migration
- Free of lead, cadmium, nickel and phthalate
- REACH<sup>3</sup> and ROHS<sup>4</sup> compliant

#### Typical Properties (Paste)

Form Pseudoplastic paste

Viscosity 30 – 50 Pas

 $(25 \, ^{\circ}\text{C}, \, D = 100/\text{s})$ 

Solids  $84.5 \% \pm 1.5 \%$ 

Printing Speed Up to 20 cm/s

Shelf Life 6 months from date of

shipment with correct storage (in a dry, cool (5 – 25 °C) and dark place with container

tightly shut).

#### Processing

1) Spatulate well prior to processing.

When stored in a refrigerator, the paste should have acquired room temperature before being opened, to avoid condensation.

- 2) Print through a 325 mesh stainless steel screen. Total thickness: approx. 75 μm.
- 3) Level at room temperature for 5 10 minutes.
- 4) Dry at 150 °C for 10 20 minutes.
- 5) Fire at 850 °C (peak) for 10 minutes, and with a total firing cycle time of c. 30 60 minutes.

#### Typical Properties (Fired)<sup>1</sup>

Fired Film Thickness<sup>2</sup>  $8.0 - 12.0 \mu m$ 

(FFT)

Line Definition  $\geq 125 \mu m$ 

Resistivity<sup>2</sup>  $\leq$  30 m $\Omega/\Box$  (FFT: 12  $\mu$ m)

Aged Adhesion (Sn96/Ag3.5/Cu0.5)

 $\geq$  20 N (48 hrs, 150 °C)

Leach Resistance (Sn96/Ag3.5/Cu0.5)

 $\geq$  2 dips (245 °C, 5 sec each)

#### Thinner

HVS 507



### **Technical Data Sheet**







#### Silver / Palladium Conductor Paste

#### Legend:

- Typical properties based on laboratory test methods. For optimum results all materials should be fired in a profiled furnace supplied with dried, hydrocarbon and other contaminant free air (PP-1).
- $^{2)}$  Measured after printing with a 325 mesh steel screen; screen thickness and emulsion thickness combined was c. 75  $\mu m,$  and the resultant printed track was 500  $\mu m$  wide.
- 3) REACH compliant according to the <u>latest</u> \*\* Annex XIV to Regulation (EC) of the European Parliament and of the council on the Registration, Evaluation, Authorisation and Restriction of Chemicals ("REACH") by European Chemicals Agency and its subsequent amendments; the <u>material does not</u> contain any substance listed in Annex XIV.
- <sup>4)</sup> RoHS compliant according to the <u>latest</u> \*\* Directives (European Union) of Restriction of Hazardous Substances ("RoHS") and its subsequent amendments (including the exceptions related to Pb)
- \* See the data sheet issue date (DD/MM/YY) as reference of validity of latest edition which is available on request

Heraeus Electronics Heraeus Deutschland GmbH & Co. KG Heraeusstraße 12 – 14 63450 Hanau, Germany www.heraeus-electronics.com Americas

Phone +1 610 825 6050 electronics.americas@heraeus.com

Asia Pacific

Phone +65 6571 7677 electronics.apac@heraeus.com China

Phone +86 21 3357 5457 electronics.china@heraeus.com

**Europe, Middle East and Africa** 

Phone +49 6181 35 3069, +49 6181 35 3627 electronics.emea@heraeus.com