## Heraeus

## **Technical Data Sheet**



# THICK FILM MATERIALS

**Product Type:** Component Metallization

**Product Name:** PCC11889







**Lead Free Silver Conductor** 

## Description

PCC11889 is a Pb and Cd free low temperature firing silver paste designed to screen print solderable electrodes onto a variety of electronic ceramic component. The fired film forms a highly adherent bond to many types of substrates, including piezoelectric transducers (PZTs), NTC thermistors, alumina, steatite, and porcelain. The metalized electrode is readily solderable for external lead attachment.

#### **Key Benefits**

- REACH<sup>1</sup> and ROHS<sup>2</sup> compliant
- Pb and Cd free
- Lower firing temperature (< 700 °C)</li>
- Designed for piezoelectric transducers (PZTs), NTC thermistors, alumina, steatite, and porcelain.

## Typical Properties

## Resistivity

 $\leq\!3.0~\text{m}\Omega/\square$  at 25  $\mu\text{m}$  fired film thickness

## Adhesion

Sn62/Pb36/Ag2 at 200 °C 0.10 in x 0.10 in pads Initial  $\geq$  6.6 lbs

#### Solderability

Sn62/Pb36/Ag2, 230 °C 2 – 3 seconds dip Excellent

#### **Viscosity**

100 – 120 Kcps, Brookfield HBT CP-51 spindle at 1 rpm, 25 °C

#### Solids (typical)

> 70 %

## Recommended Processing Guidelines

#### Printing

60 - 200 stainless steel mesh screen 0.7 - 1.0 mil emulsion

#### Drying

150 °C for 10 - 15 minutes

#### **Firing**

Optimum firing parameters depend on substrate composition  $550-700\,^{\circ}\text{C}$  peak firing temperature Dwell time of 8-12 minutes Total cycle time of 45-60 minutes Larger parts may require a longer firing profile

#### **Thickness**

Fired  $10 - 14 \mu m$ 

## **Thinner**

RV-252

#### Warranty

Material guaranteed to meet specifications for 6 months from date of shipment.

### Storage

Store in a dry location at 5-25 °C.

#### DO NOT REFRIGERATE.

Allow paste to come to room temperature prior to opening. Spatulate well before using, as settling may occur during storage.



## **Technical Data Sheet**







#### **Lead Free Silver Conductor**

#### Legend:

- 1) REACH compliant according to the <u>latest</u>
  \*\* Annex XIV to Regulation (EC) of the
  European Parliament and of the council on
  the Registration, Evaluation, Authorisation and
  Restriction of Chemicals ("REACH") by
  European Chemicals Agency and its
  subsequent amendments; the material does not
  contain any substance listed in Annex XIV.
- <sup>2)</sup> RoHS compliant according to the <u>latest</u> \*\* Directives (European Union) of Restriction of Hazardous Substances ("RoHS") and its subsequent amendments (including the exceptions related to Pb).
- \* See the data sheet issue date (DD/MM/YY) as reference of validity of latest edition which is available on request

Heraeus Electronics

Heraeus Deutschland GmbH & Co. KG Heraeusstraße 12 – 14 63450 Hanau, Germany www.heraeus-electronics.com Americas

Phone +1 610 825 6050 electronics.americas@heraeus.com

Asia Pacific

Phone +65 6571 7677 electronics.apac@heraeus.com China

Phone +86 21 3357 5457 electronics.china@heraeus.com

Europe, Middle East and Africa

Phone +49 6181 35 3069, +49 6181 35 3627 electronics.emea@heraeus.com