

## Technical Data Sheet

### THICK FILM MATERIALS

Product Type: LTCC Materials

Product Name: X200W



#### White LTCC Dielectric Powder

##### Description

Heraeus' X-200W LTCC powder mix is designed to be cast into green tape used for module and passive component applications. In these applications the relatively low permittivity and low loss of this material allow for the production of high performance components and multilayer circuits.

X-200W is compatible with binder systems typically used in tape fabrication. In tape form this material is also compatible with Heraeus' silver and gold conductor systems.

##### Key Benefits

- REACH<sup>1</sup> and ROHS<sup>2</sup> compliant
- Silver conductor compatible
- Lead and cadmium free
- High Q
- Near zero  $T_f$  (temperature coefficient of frequency)

##### Typical Properties (Powder)

Particle Size	D90: 5.0 – 7.0 $\mu\text{m}$ D50: 2.25 – 3.25 $\mu\text{m}$
Surface Area	2.4 – 3.0 $\text{m}^2/\text{g}$
Fired Density	3.0 – 3.2 $\text{g}/\text{cm}^3$

##### Burnout and Firing in a Box Oven

Heating Rate	5 – 5.5 $^{\circ}\text{C}/\text{min}$
Peak Temperature	870 – 880 $^{\circ}\text{C}$
Dwell Time at Peak	20 – 30 mins
Cooling Rate	~ 3 – 6 $^{\circ}\text{C}/\text{min}$
Setter	96 % alumina

##### Typical Fired Properties

Dielectric Constant at 30 MHz, 25 $^{\circ}\text{C}^*$	8.8 – 9.5
Dissipation Factor at 30 MHz	$\leq 2 \times 10^{-3}$
Thermal Coefficient of Expansion (25 – 300 $^{\circ}\text{C}$ )	5.6 $\text{ppm}/^{\circ}\text{C}$
Breakdown Voltage	> 1 kV at 25 $\mu\text{m}$
Insulation Resistance (at 25 $^{\circ}\text{C}$ )	> $10^{13} \Omega\text{cm}$
Thermal Coefficient of Frequency ( $T_f$ ) (-40 – 80 $^{\circ}\text{C}$ )	< 10 $\text{ppm}/^{\circ}\text{C}$
Thermal Conductivity	3 W/mK

\*30 MHz data measured on pressed disc, ~20mm diameter x 1.7 mm thick.

## Technical Data Sheet



### White LTCC Dielectric Powder

#### Legend:

1) REACH compliant according to the latest \*\* Annex XIV to Regulation (EC) of the European Parliament and of the council on the Registration, Evaluation, Authorisation and Restriction of Chemicals ("REACH") by European Chemicals Agency and its subsequent amendments; the material does not contain any substance listed in Annex XIV.

2) RoHS compliant according to the latest \*\* Directives (European Union) of Restriction of Hazardous Substances ("RoHS") and its subsequent amendments (including the exceptions related to Pb)

\* See the data sheet issue date (DD/MM/YY) as reference of validity of latest edition which is available on request

**Heraeus Electronics**  
Heraeus Deutschland GmbH & Co. KG  
Heraeusstraße 12 – 14  
63450 Hanau, Germany  
www.heraeus-electronics.com

**Americas**  
Phone +1 610 825 6050  
electronics.americas@heraeus.com

**China**  
Phone +86 21 3357 5457  
electronics.china@heraeus.com

**Asia Pacific**  
Phone +65 6571 7677  
electronics.apac@heraeus.com

**Europe, Middle East and Africa**  
Phone +49 6181 35 3069, +49 6181 35 3627  
electronics.emea@heraeus.com