

## Technical Data Sheet



### THICK FILM MATERIALS

**Product Type:** Conductors

**Product Name:** C2130B



#### Pb and Cd Free Silver/Palladium Conductor

##### Description

C2130B is a Pb, Cd and Ni free Pd/Ag composition designed for applications where more leach resistance is required. The C2130B conductor is suitable for a wide variety of applications such as automotive electronics, power hybrids and commercial circuits where more stringent requirements exist. It exhibits excellent solderability, aged adhesion and is aluminum wire bondable.

##### Key Benefits

- Excellent solderability and leach resistance
- Excellent long term adhesion
- Pb, Cd and Ni free
- Good Al wire bond adhesion (initial and aged)

##### Typical Properties

###### Resistivity:

≤ 35 mΩ/□ at 12 μm fired film thickness

###### Viscosity:

180 – 280 Kcps Brookfield HBT  
SC4 – 14 spindle, 6R utility cup at 10 rpm, 25 °C

###### Solids:

79.0 ± 1.0 %

###### Solderability:

Sn62/Pb36/Ag2 at 230 °C, RMA flux  
100 % for 5 second dip

###### Solder Leaching:

Sn62/Pb36/Ag2 at 225 °C, RMA flux  
≥ 6 dips (10 seconds for each dip)

###### Adhesion:

80 x 80 mil pad  
Sn62/Pb36/Ag2 at 225 – 230 °C  
Forced air box oven

Initial: ≥ 5.0 lbs  
48 hours @ 150 °C: ≥ 5.0 lbs

###### Wire Bond Adhesion:

10 mil Al wire, 99.999 % Al, Elongation > 5 %  
5 x 850 °C firing  
Initial: ≥ 450.0 g  
1000 hours @ 150 °C: ≥ 400.0 g

##### Recommended Processing Guidelines

###### Printing:

280 – 325 mesh stainless steel screen  
0.5 mil emulsion  
Allow to level at room temperature for 5 – 10 minutes before drying

###### Printing Speed:

Up to 7 in/sec

###### Coverage:

75 cm<sup>2</sup>/g at 12 μm fired film thickness

###### Drying:

150 °C for 10 to 15 minutes

###### Firing:

850 °C peak temperature  
10 minutes at peak  
Total cycle time 30 – 60 minutes

###### Film Thickness:

Wet: 35 – 37 μm  
Fired: 10 – 15 μm

###### Line Definition:

≥ 6 mils (150 μm)

###### Thinner:

RV-372

###### Warranty:

Material guaranteed to meet specifications for 6 months from date of shipment.

###### Storage:

Store in a dry location at 5 – 25 °C.

###### DO NOT REFRIGERATE.

Allow paste to come to room temperature prior to opening.  
Spatulate well before using, as settling may occur during storage.

## Technical Data Sheet



### Pb and Cd Free Silver/Palladium Conductor

#### Legend:

1) REACH compliant according to the latest \* Annex XIV to Regulation (EC) of the European Parliament and of the council on the Registration, Evaluation, Authorisation and Restriction of Chemicals ("REACH") by European Chemicals Agency and its subsequent amendments; the material does not contain any substance listed in Annex XIV.

2) RoHS compliant according to the latest \* Directives (European Union) of Restriction of Hazardous Substances ("RoHS") and its subsequent amendments (including the exceptions related to Pb)

**Heraeus Electronics**  
Heraeus Deutschland GmbH & Co. KG  
Heraeusstraße 12 – 14  
63450 Hanau, Germany  
[www.heraeus-electronics.com](http://www.heraeus-electronics.com)

**Americas**  
Phone +1 610 825 6050  
[electronics.americas@heraeus.com](mailto:electronics.americas@heraeus.com)

**China**  
Phone +86 53 5815 9601  
[electronics.china@heraeus.com](mailto:electronics.china@heraeus.com)

**Asia Pacific**  
Phone +65 6571 7649  
[electronics.apac@heraeus.com](mailto:electronics.apac@heraeus.com)

**Europe, Middle East and Africa**  
Phone +49 6181 35 4370  
[electronics.emea@heraeus.com](mailto:electronics.emea@heraeus.com)