

Technical Data Sheet

THICK FILM MATERIALS

Product Type: Conductors

Product Name: C6011

AuPdPt Conductor Paste for Fuel Sensors

Description

C6011 is a screen printable, non solderable Gold / Palladium / Platinum conductor paste for fuel sensor applications.

C6011 is optimized in hardness and surface density. It shows excellent printability resulting in high line definition and smooth surface under various drying conditions.

C6011 is not foreseen for soldering process.

Key Benefits

- Most suitable material for low sulphur fuel application because of absence of silver
- Very smooth fired surface which exhibits very durable mechanical resistance and chemically extremely resistant
- Free of cadmium and nickel

Processing

- 1) Spatulate well prior to processing.

When stored in a refrigerator, allow paste to come to room temperature prior to opening, to avoid condensation.

- 2) Print through a 200 – 325 mesh stainless steel screen. 0.03 – 0.04 mm Ø wire and 20 – 30 µm emulsion.
- 3) Level at room temperature for 10 minutes.
- 4) Dry at max. 150 °C for 8 – 10 minutes.
- 5) Fire at 850 °C (peak) for 10 minutes, and with a total firing cycle time of c. 30 – 60 minutes.

Thinner

HVS 100

Typical Properties (Paste)

| | |
|------------|--|
| Form | Pseudoplastic paste |
| Viscosity | 25 – 45 Pas (25 °C, D = 100/s) |
| Solids | 84.0 % ± 1.5 % |
| Coverage | c. 75 cm ² /g (at FFT 10 µm) |
| Shelf Life | 6 months from date of shipment with correct storage (in a dry, cool (5 – 25 °C) and dark place with container tightly shut). |

Typical Properties (Fired)¹

| | |
|---|-------------------------|
| Fired Film Thickness ² (FFT) | 8 – 14 µm |
| Line Definition | ≥ 125 µm |
| Resistivity ² | ≤ 100 mΩ/□ (FFT: 10 µm) |
| Solderability | Not solderable |

Technical Data Sheet

AuPdPt Conductor Paste for Fuel Sensors

Legend:

1) Typical properties based on laboratory test methods. For optimum results all materials should be fired in a profiled furnace supplied with dried, hydrocarbon and other contaminant free air (PP-1).

2) Measured after printing with a 325 mesh steel screen; screen thickness and emulsion thickness combined was c. 75 μm , and the resultant printed track was 500 μm wide.

* See the data sheet issue date (DD/MM/YY) as reference of validity of latest edition which is available on request

Heraeus Electronics
Heraeus Deutschland GmbH & Co. KG
Heraeusstraße 12 – 14
63450 Hanau, Germany
www.heraeus-electronics.com

Americas
Phone +1 610 825 6050
electronics.americas@heraeus.com

China
Phone +86 53 5815 9601
electronics.china@heraeus.com

Asia Pacific
Phone +65 6571 7649
electronics.apac@heraeus.com

Europe, Middle East and Africa
Phone +49 6181 35 4370
electronics.emea@heraeus.com