

Technical Data Sheet



Product Type: Dielectrics Product Name: IP9038A



Pb and Cd Free Resistor Overglaze

Description

IP9038A is a Pb, Cd and Ni free green overglaze designed for printing and firing over thick film resistors. IP9038A provides improved trimmed resistor stability and environmental protection.

IP9038A has been proven to withstand plating solutions. IP9038A has excellent process insensitivity and is compatible with all Heraeus air-fireable resistor series.

IP9038A is available in white as well (IP9038White).

Key Benefits

- Minimizes resistance shift on refire
- Pinhole free
- Single coat application
- Resistant to plating solutions

Typical Properties

Coverage

160 cm²/g at 10 μm fired film thickness

Viscosity

140 – 180 Kcps, Brookfield HBT, SC4-14 spindle and 6R utility cup at 10 rpm, 25 °C

Solids 75.0 ± 2.0 %

Heraeus Electronics Heraeus Deutschland GmbH & Co. KG Heraeusstraße 12 – 14 63450 Hanau, Germany www.heraeus-electronics.com Americas Phone +1 610 825 6050 electronics.americas@heraeus.com

Asia Pacific Phone +65 6571 7649 electronics.apac@heraeus.com

Recommended Processing Guidelines

Printing

280 – 325 mesh stainless steel screen 0.5 mil emulsion 1.1 mil wire

Drying

Allow to level for 10 minutes before drying 150 °C for 10 minutes

Firing

 $500 \degree C (6 - 8 \text{ minutes})$ Dwell time 520 $\degree C (4 - 6 \text{ minutes})$ Dwell time

Thickness

Dried: Fired:

Thinner

RV-372

Warranty

Material guaranteed to meet specifications for 6 months from date of shipment.

 $\frac{18-22}{10}\,\mu\text{m}$

Storage

Store in a dry location at 5 – 25 °C. **DO NOT REFRIGERATE.**

Allow paste to come to room temperature prior to opening. Spatulate well before using, as settling may occur during storage.

China

Phone +86 53 5815 9601 electronics.china@heraeus.com

Europe, Middle East and Africa Phone +49 6181 35 4370 electronics.emea@heraeus.com

The descriptions and engineering data shown here have been compiled by Heraeus using commonly-accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use any patient infingement resulting from its use (indires this is consticutad) and expectibility agreed to writing, in advance). The data is supplied to not request to that the user shall conduct tests to determine materials sublability for particular applications.