Heraeus

AluBond AlW49P Large Diameter Aluminum Wedge Bonding Wire

Excellent Thermal and Electrical Conductivity

AluBond AlW49P wire has excellent thermal and electrical conductivity and can be used on all heavy wire wedge bonding equipment. While normally supplied in an annealed state, Heraeus can also supply AluBond AlW49P aluminum wedge bonding wire to meet mechanical specifications best suited to your equipment and the looping requirements of your application. Various spool colors are available that enable customization of wire diameter and spool color. Larger traverse dimension on spool allows for 2X wire length resulting in higher UPH.

AluBond AIW49P Benefits

- Larger diameters suitable for power packages and discrete devices
- 3mil 20mil thickness range prevents sag or deflection during molding
- Chemicals and metallurgical behavior compatible with aluminum metallization
- Bondable at temperature and energy levels low enough to avoid damage to sensitive devices
- Enhance corrosion resistance designed for nonhermetically sealed pacakages

Areas of Application

- Automotive components
- Power components
- Hybrid components
- Transistors / Thyristors
- Battery cell connecting





Recommended Technical Data of AluBond AlW49P								
Diameter	Microns	125	150	200	250	300	380	500
	Mils	5	6	8	10	12	15	20
Elogation	(%)	> 5	> 5	> 5	> 10	> 10	> 10	> 10
Breaking Load	(g)	100 - 150	130 - 190	200 - 350	300 - 450	450 - 700	700 - 1100	1200 - 2000

For other diameters, please contact Heraeus Bonding Wires sales representative.

Wire Specification

Chemical Composition				
Aluminum	99.99%			
Total Impurities:	0.01%			

Physical Properties

Density	2.70 g/cm ³
Melting Point	660°C / 1220°F
Electrical Resistivity @20°C	2.7 µW/cm
Thermal Conductivity @20°C	230 W/m.K
Electrical Conductivity @20°C	64% IACS



Heraeus Electronics Heraeus Deutschland GmbH & Co. KG Heraeusstraße 12-14 63450 Hanau, Germany www.heraeus-electronics.com Americas Phone +1 610 825 6050 electronics.americas@heraeus.com

Asia Pacific Phone +65 6571 7677 electronics.apac@heraeus.com **China** Phone +86 21 3357 5457 electronics.china@heraeus.com

Europe, Middle East and Africa Phone +49 6181 35 3069 +49 6181 35 3627 electronics.emea@heraeus.com

The descriptions and engineering data shown here have been compiled by Heraeus using commonly-accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for particular application.