



Bright Gold Paste for direct screen printing on glass GGP 1229D-10% H

1 General Information

GGP 1229D-10% H is a wet paste for direct screen printing on glass, which is typically used for the decoration of cosmetic containers. The material has a moderate printing viscosity, similar to GGP 1242D H. Gold decorations created with GGP 1229D-10% H have a lemon yellow gold colour shade.

2 Standard Firing Range

| Substrate | Firing range |
|--------------------------------------|--------------|
| Cosmetic container glass (soda-lime) | 560 – 620°C |
| | |

The firing result depends on the firing temperature, on the total firing time, the soak time and not least on the glass type. To achieve an optimized firing result, we therefore recommend a firing test under the users own individual conditions.

3 Properties of the preparations

The major characteristics of a Heraeus precious metal preparation are determined by its production recipe. From each lot produced, we take a sample and check defined characteristics.

In case of screen-printing preparations, before firing, we check the physical properties (e.g. viscosity, thixotropy) and the printing properties compared to a predefined standard. After firing under standard firing conditions, we check the gold colour shade and the adhesion to the substrate. Controlling each single production lot assures the highest product quality and lot-to-lot consistency.



3.1 Processing

We supply bright precious metal preparations for direct screen printing ready to use. GGP 1229D H has a thixotropic nature, means the typical printing viscosity is reached at certain printing speed, when the thixotropy is temporarily broken. The applied material hardens instantly and assure a sharp outline of the print.

3.2 Storage

Printing pastes are subject to an ageing process. Therefore, we recommend using the material within 9 months. The material should be stored at room temperature (20°C). Cool storage – but no freezing – has a positive impact on the shelf life.

3.3 Consumption

The material consumption depends on the thickness of the applied precious metal layer. Under our conditions, the consumption is approx. 0,15 to 0,30g/100 cm².*

The statements concerning our products correspond to our current knowledge and experience. It is the obligation of the purchaser to examine the usefulness of the products in its intended use in each individual case. In order to prevent production losses the user has to test the preparations in connection with every other material being involved in the production process and has to be satisfied that the intended result can be consistently produced.

4 Properties of finished decorations

The properties of finished decorations are influenced by a number of factors which interact with each other: The precious metal preparation used, possible bordering colours, application, substrate, possible substrate treatment and last but not least the firing conditions. We processed GGP1229D-10% H under defined, standard test conditions and run certain tests of the achieved precious metal decoration.

4.1 Abrasion resistance

In tests decorations created with GGP 1229D-10% H showed a good abrasion resistance.

4.2 Oxydation resistance

As a lemon yellow gold GGP 1229D-10% H contain a fair amount of silver. Under unfavourable storage conditions silver containing precious metal decorations can tarnish in the course of time. Especially the contact to cardboard boxes, high humidity and high temperature support the reaction of silver to silver sulphide.

5 Application recommendations

5.1 Preparation of the substrate to be decorated

- Make sure that the surface of the object to be decorated is clean and dry. Dust, fingerprints and water condensation can affect the decoration while firing.
- Take care that the objects to be decorated are not taken from a cold store into a warm shop. A fine condensation film may occur, which is not visible to the naked eye. This results in firing disturbance (pinholes) in the fired precious metal decoration. Allow enough time so that they can adjust to the decoration room temperature.

5.2 Application of the paste

- Work in a well-ventilated room. Good printing conditions occur at a room temperature of 20 to 25°C.
- We recommend printing GGP 1229D-10% H with a 120-34 to 140-34T polyester screen.
- For a good printing result, it is important to have a well sharpened squeegee (hardness: 60-75° shore).

5.3 Firing

- During the first heating phase the organic components of the preparation burn off. This process is completed at approx. 400°C. The gold film is formed. A constant, slow temperature increase, enough oxygen and sufficient ventilation are decisive for the quality of the fired precious metal decoration.
- The firing profile considerably influences the mechanical and chemical properties of the fired decoration.
- The rate of cooling has no major influence on the quality of the gold decoration, unlike the firing temperature and soak time. However, the firing process should not be stopped too abruptly after the soak time. If the rate of cooling is too fast, there may be a danger of damaging the article (cracks and broken glass).

6 Typical defects, root causes and countermeasures to prevent them

| Defect | Possible cause | Countermeasure |
|--|---|--|
| Streaks in the printed precious metal film | The squeegee is possibly scratched | Exchange or sharpen the squeegee |
| Squashed print | The squeegee is not sharp enough or it is worn out | Exchange or sharpen the squeegee |
| Spots, firing disturbance | Objects were soiled by dust, finger marks or water drops before printing | clean the object before decorating |
| | Problems in the kiln such as: <ul style="list-style-type: none"> • furnace atmosphere reduction • insufficient ventilation • too quick heat up in the critical phase between 200-400°C • too many objects in the kiln | <ul style="list-style-type: none"> • increase air addition • improve ventilation • reduce the heating speed • reduce the number of objects in the kiln |
| Fired result is blotchy or matt | Screen used is too coarse; printed layer is too thick | We recommend a 120-34 to 140-34 T polyester screen. |
| Blurred outline after firing (spreading or running) | Too many objects in the kiln | Reduce the number of objects in the kiln |
| Precious metal flakes off during firing | Printed layer was too thick. | Reduce thickness of applied film. |
| Fine pinholes | Moisture on the objects before decoration leads to firing faults (pinholes) | Give the ware enough time to acclimate to the temperature of the decoration shop and so a possible condensation film to evaporate |
| Low mechanical resistance of the precious metal decoration | Too low firing temperature | Increase the firing thickness |
| | The layer of the preparation is too thin | The use a 120-34 to 140-34T polyester screen contributes to a reasonable layer thickness after firing. |