

RL PT M603B H



Platinum Resinate Solution / DPIS*

* Development Product Information Sheet

Description

RL PT M603B H is a liquid precious metal solution and it contains platinum in form of dissolved organo-metallic compound.

Key benefits

- Suitable to use as additive for thick film and organo-metallic pastes
- Free of lead, cadmium and nickel
- Free of phthalate
- REACH ¹ and RoHS ² compliant

Processing

1. When stored in a refrigerator allow product to come to room temperature prior to opening, to avoid condensation.
2. The solution is miscible with halogenated hydrocarbons, some higher alcohols (e.g. Terpineol), esters and ketones (e.g. Cyclohexanone). Not miscible with aliphatic and aromatic hydrocarbons, lower alcohols, esters and ketones.

Thinner: HVS 100
Toluene
Cyclohexanone

Typical Properties (Solution):

Form:	Dark brown liquid
Viscosity:	50 - 1000 mPas (25 °C, 60 rpm)
Chemical Characterisation:	Platinum sulforesinate in a mixture of organic solvents
Platinum Content ³ :	14.0 ± 0.2 %
Calculated Residue:	Corresponds to platinum content
Coverage:	Not applicable
Shelf Life:	6 months from date of shipment with correct storage (in a dry, cool (5 – 25 °C) and dark place with container tightly shut)

RL PT M603B H



Platinum Resinate Solution / DPIS*

* Development Product Information Sheet

- 1 REACH compliant according to the latest ** Annex XIV to Regulation (EC) of the European Parliament and of the council on the Registration, Evaluation, Authorisation and Restriction of Chemicals ("REACH") by European Chemicals Agency and its subsequent amendments; the material does not contain any substance listed in Annex XIV.
- 2 RoHS compliant according to the latest ** Directives (European Union) of Restriction of Hazardous Substances ("RoHS") and its subsequent amendments (including the exceptions related to Pb)
- 3 Inductively coupled plasma optical emission spectrometry (ICP-OES), also referred to as inductively coupled plasma atomic emission spectroscopy (ICP-AES), is an analytical technique used for the detection of trace metals.

** See the data sheet issue date (DD/MM/YY) as reference of validity of latest edition which is available on request.

The descriptions and engineering data shown here have been compiled by Heraeus using commonly-accepted procedures, in conjunction with the latest equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The user shall conduct tests to determine materials suitability for a particular application.

Heraeus Deutschland
GmbH & Co. KG
Heraeus Performance Products
BL Precious Colours
Heraeusstr. 12 – 14
63450 Hanau, Germany
E-Mail: preciouscolours@heraeus.com