

## Resinates

### RL RH 8826 H



### Rhodium Metallo Organic Solution / DPIS\*

\* Development Product Information Sheet

#### Description

RL RH 8826 H contains rhodium in form of dissolved organo-metallic compound.

#### Key Benefits

- Suitable to use as additive for thick film and organo-metallic pastes
- Free of lead, cadmium and nickel
- Free of phthalate
- REACH <sup>1</sup> and RoHS <sup>2</sup> compliant

#### Processing

1. When stored in a refrigerator allow product to come to room temperature prior to opening, to avoid condensation.
2. The solution is miscible with most common organic solvents.

#### Thinner

HVS 100  
Toluene  
Cyclohexanone

#### Typical Properties (Solution)

Form:	Dark amber to brown solution
Viscosity:	170 - 390 mPas (25 °C, 30 rpm)
Chem. Characterization:	Rhodium carboxylate in organic solvents
Metal Content <sup>3</sup> :	10.0 ± 0.1 % Rh
Calcinated Residue:	12.35 ± 0.15 % Rh <sub>2</sub> O <sub>3</sub>
Coverage:	Not applicable
Shelf Life:	6 months from date of shipment with correct storage (in a dry, cool (5 – 25 °C) and dark place with container tightly shut)

## Resinates

RL RH 8826 H



## Rhodium Metallo Organic Solution / DPIS\*

\* Development Product Information Sheet

- 1 REACH compliant according to the latest \*\* Annex XIV to Regulation (EC) of the European Parliament and of the council on the Registration, Evaluation, Authorisation and Restriction of Chemicals ("REACH") by European Chemicals Agency and its subsequent amendments; the material does not contain any substance listed in Annex XIV.
- 2 RoHS compliant according to the latest \*\* Directives (European Union) of Restriction of Hazardous Substances ("RoHS") and its subsequent amendments (including the exceptions related to Pb)
- 3 Inductively coupled plasma optical emission spectrometry (ICP-OES), also referred to as Inductively coupled plasma atomic emission spectroscopy (ICP-AES), is an analytical technique used for the detection of trace metals

\*\* See the data sheet issue date (DD/MM/YY) as reference of validity of latest edition which is available on request.

---

The descriptions and engineering data shown here have been compiled by Heraeus using commonly-accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for a particular application.

Heraeus Deutschland  
GmbH & Co. KG  
Heraeus Performance Products  
BL Precious Colours  
Heraeusstr. 12 – 14  
63450 Hanau, Germany  
E-Mail: [preciouscolours@heraeus.com](mailto:preciouscolours@heraeus.com)