

Resinates

RP Au 130410 – 9%



Gold Resinate Paste / DPIS*

* Development Product Information Sheet

Description

RP Au 130410-9% is a thin film conductor paste for use on alumina and glazed alumina. It contains gold and a small amount of non-precious metals in form of soluble organo-metallic compounds. After firing a conducting gold film is obtained.

Key Benefits

- Due to simultaneous sintering of non-precious metal oxides it offers a high adhesion on above mentioned substrates.
- To reach higher film thicknesses it is necessary to print several layers on top of each other. Each applied layer has to be fired separately.
- Free of lead, cadmium and nickel
- Free of phthalate
- REACH³ and RoHS⁴ compliant

Processing

1. Spatulate well prior to processing.

When stored in a refrigerator allow paste to come to room temperature prior to opening, to avoid condensation.

2. Print through a 300 – 350 mesh stainless steel screen with an emulsion thickness of 15 – 20 µm.
3. Let the print settle at room temperature for 10 minutes.
4. Dry at 90 to 120 °C for 15 minutes. Do not exceed peak of 130 °C.
5. Fire at 850 °C (peak) for 7 – 10 minutes and with a total firing cycle time of 40 - 60 minutes.

Thinner

HVS 100

Typical Properties (Paste)

Form:	Thixotropic paste
Viscosity:	6.0 – 9.0 Pas (20 °C, D = 500 s ⁻¹)
Au Content:	9.0 % ± 0.3 %
Printing Speed:	Up to at least 10 cm/s
Coverage: (325 mesh screen)	Approx. 400 cm ² / g (FFT @ 0.4 µm)
Shelf Life:	6 months from date of shipment with correct storage (in a dry, cool (5 - 25 °C) and dark place with container tightly shut)

Typical Properties (Fired)¹

Fired Film Thickness ² : (FFT)	0.1 - 0.5 µm
Line Definition:	≥ 150 µm (width and space)
Resistivity ² : (25 °C, DFT ⁵ @ 10 µm)	200 – 500 mΩ/□

Screen Cleaning

Toluene
Xylene
Stoddard solvent

Note:

After printing, screens should be cleaned immediately to avoid drying of remained paste on the screen.

Resinates

RP Au 130410 – 9%



Gold Resinate Paste / DPIS*

* Development Product Information Sheet

- 1 Typical properties based on laboratory test methods. For optimum results all materials should be fired in a profiled furnace supplied with dried, hydrocarbon and other contaminant free air (PP-1).
 - 2 Measured on alumina 96% after printing with a 325 mesh steel screen; thickness of screen and emulsion combined was c. 15 µm, and the resultant printed track was 500 µm wide.
 - 3 REACH compliant according to the latest ** Annex XIV to Regulation (EC) of the European Parliament and of the council on the Registration, Evaluation, Authorisation and Restriction of Chemicals ("REACH") by European Chemicals Agency and its subsequent amendments: the material does not contain any substance listed in Annex XIV.
 - 4 RoHS compliant according to the latest ** Directives (European Union) of Restriction of Hazardous Substances ("RoHS") and its subsequent amendments (including the exceptions related to Pb)
 - 5 DFT: Dried Film Thickness; FFT: Fired Film Thickness
- ** See the data sheet issue date (DD/MM/YY) as reference of validity of latest edition which is available on request.

The descriptions and engineering data shown here have been compiled by Heraeus using commonly-accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for a particular application.

Heraeus Deutschland
GmbH & Co. KG
Heraeus Performance Products
BL Precious Colours
Heraeusstr. 12 – 14
63450 Hanau, Germany
E-Mail: preciouscolours@heraeus.com