

Resinates

RP RH MR 4504-P H



Rhodium Resinate Powder / DPIS*

* Development Product Information Sheet

Description

RP RH MR 4504-P H is a precious metal product. It contains rhodium in form of an organometallic compound.

Key Benefits

- Additive for thick film pastes and also for organo-metallic pastes
- Free of lead, cadmium and nickel
- REACH ¹ and RoHS ² compliant

Processing

1. When stored in a refrigerator allow product to come to room temperature prior to opening, to avoid condensation.
2. Soluble in most common organic solvents

Typical Properties (Powder)

Form:	Green powder
Chem. Characterization:	Rhodium carboxylate
Rhodium Content ³ :	24.0 ± 1.5 %
Calcinated Residue:	29.5 ± 2.0 % (calculated)
Shelf Life:	12 months from date of shipment with correct storage (in a dry, cool (5 - 25 °C) and dark place with the container tightly shut).

Thinner

HVS 100
Cyclohexanone

RP RH MR 4504-P H



Rhodium Resinate Powder / DPIS*

* Development Product Information Sheet

- 1 REACH compliant according to the latest ** Annex XIV to Regulation (EC) of the European Parliament and of the council on the Registration, Evaluation, Authorisation and Restriction of Chemicals ("REACH") by European Chemicals Agency and its subsequent amendments: the material does not contain any substance listed in Annex XIV.
- 2 RoHS compliant according to the latest ** Directives (European Union) of Restriction of Hazardous Substances ("RoHS") and its subsequent amendments (including the exceptions related to Pb)
- 3 Inductively coupled plasma optical emission spectrometry (ICP-OES), also referred to as inductively coupled plasma atomic emission spectroscopy (ICP-AES), is an analytical technique used for the detection of trace metals.

** See the data sheet issue date (DD/MM/YY) as reference of validity of latest edition which is available on request.

The descriptions and engineering data shown here have been compiled by Heraeus using commonly-accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for a particular application.

Heraeus Deutschland
GmbH & Co. KG
Heraeus Performance Products
BL Precious Colours
Heraeusstr. 12 – 14
63450 Hanau, Germany
E-Mail: preciouscolours@heraeus.com